

In the Specification:

On page 7, amend the paragraph beginning on line 5 as follows:

One feature of a sufficiently low level of the NT LT modification and foreign phases is a full width at half maximum (FWHM) of the emission of less than 90 nm, since the lower the level of foreign phases, the lower the proportion of the specific orange-red emission from the modification which is rich in foreign phases, in particular the nitridosilicate foreign phases Sr-Si-N-Eu such as in particular $\text{Sr}_2\text{Si}_5\text{N}_8\text{:Eu}$.